



FB-31 POLYAMINE

DESCRIPTION: FB-31 POLYAMINE is an extremely low viscosity light colored cycloaliphatic curing agent designed for construction and civil engineering applications. It is intended for use with liquid and solid A epoxy resins. FB-31 Polyamine is compatible with most aliphatic and cycloaliphatic amine curing agents.

FEATURES

- ***Virtually No Odor***
- ***Excellent Color Stability***
- ***Outstanding Adhesion to Concrete***
- ***Water Spot Resistant***
- ***Chemical Resistant***

SUGGESTED USES

- ***High Solids Coatings***
- ***Chemical Resistant Coatings***
- ***Seamless Flooring***
 - ***Broadcast***
 - ***Trowel Down***
 - ***Slurry Broadcast***

FB-31 Polyamine Properties

Viscosity:	200
Density(lbs/gal):	8.4
Equivalent Weight:	86
Color, Gardner	1
PHR, 190 EEW Epoxy	46
Flash Point, Seta F	>200

ENVIRONMENTAL SAFETY PRECAUTIONS:

(Industrial Use Only) Corrosive. Contains amines. Contact with eyes or skin may cause severe burns. Can cause sensitization after prolonged or repeated use. Use of safety goggles and chemical resistant gloves is highly recommended. Use only with adequate ventilation.

First Aid: In case of skin contact, wash immediately and thoroughly with soap and water. For eye contact, flush immediately with plenty of water for at least 15 minutes. Consult physician immediately. For respiratory problems, remove person to fresh air.

Typical Properties

Mix ratio with 190 EEW Liquid Epoxy, phr	46
Gel Time (200 gram mass), mins	46
Tack Free Time, hours	5
Through Cure Time, hours	10
Compressive Strength (ASTM D695), psi 7 Days (neat resin)	11,450
Tensile Properties (ASTM D638) Ultimate Strength @ 14 days, psi	7,950
Elongation at break, %	5.4
Water Absorption (ASTM D570) 7 day, 24 hour immersion, %	0.4

Chemical Resistance:

Anti freeze	10% Sodium Hydroxide
Beer	50% Sodium Hydroxide
Castor oil	25% Sulfuric Acid
5% Citric acid	Xylene
Crude oil	water
25% Hydrochloric acid	wine

Data presented are typical laboratory values.

Disposal: Collect with absorbent material. Dispose of in accordance with current local, state and federal regulations.

TECHNICAL SUPPORT:

EPOXY CHEMICALS INC.

3835 State Route 72

Kirkland, Illinois 60146

www.epoxychemicals.com

Phone: 815-522-2308,

FAX: 815-522-9041

e-mail: info@epoxychemicals.com



WARRANTIES: Seller warrants that the Products do not infringe upon any copyright, patent, or trademark or trade secret, nor violate the proprietary information rights of any third party. Seller warrants that its Products will conform to and perform in accordance with the Products' specifications. THE FOREGOING WARRANTIES, ARE IN LIEU OF ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THOSE CONCERNING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. LIMITATION ON LIABILITIES: Because of the difficulty of ascertaining and measuring damages hereunder, it is agreed that, except for claims for bodily injury. Seller's liability to the Buyer or any third party, for any losses or damages, whether direct or otherwise, arising out of the purchase of Product from Seller by Buyer shall not exceed the total amount billed and billable to the Buyer for the Product hereunder. IN NO EVENT WILL SELLER BE LIABLE FOR ANY LOSS OF PROFITS OR OTHER SPECIAL OR CONSEQUENTIAL DAMAGES, EVEN IF SELLER HAS BEEN ADVISED OF THE POSSIBILITY OF SUCH DAMAGES.

3/2005