

Product Technical Data Sheet

APPLICATIONS

- Construction Adhesives
- Hardened Concrete Adhesives
- Injection Resin
- DOT Epoxies
- ASTM 881 Resin Systems

FEATURES AND BENEFITS

- Virtually No Odor
- Outstanding Adhesion to Concrete
- 1:1 mix ratio
- High Strength
- Excellent Damp Adhesion



3835 State Route 72
Kirkland, Illinois 60146

www.epoxychemicals.com

Phone: 815-522-2308

FAX: 815-522-9041

e-mail: info@epoxychemicals.com

A-6 POLYAMINE

A-6 POLYAMINE is an amine curing agent ideally suited for use in epoxy construction adhesives. It is intended for use with liquid epoxy resins at room temperature. **A-6 POLYAMINE** is compatible with most aliphatic and cycloaliphatic amine curing agents.

A-6 POLYAMINE Properties

Appearance:	Straw Color
Viscosity(cps)	5,500
Density(lbs/gal):	8.6
Equivalent Weight:	178
PHR, 190 EEW Epoxy	94

Typical Physical Properties

Liquid Epoxy Resin (190 EEW)	100
A-6 Polyamine	94
Gel Time (200g.), mins	33
Tack Free, 75F, hrs	4-5
Compressive Strength (ASTM D695), psi 7 days (neat resin)	12,540
Compressive Strength (ASTM C109), psi 7 days (mortar)	12,850
Bond Strength (ASTM C882), psi Hardened to Hardened Concrete	
2 day (moist cure)	2,125
14 day (dry cure)	3,215
Fresh Concrete to Hardened Concrete	
2 day (moist cure)	2,215
14 day (moist cure)	2,585

Data presented are typical laboratory values.

Product Technical Data Sheet



DISPOSAL: Collect with absorbent material. Dispose of in accordance with current local, state and federal regulations

FIRST AID: In case of skin contact, wash immediately and thoroughly with soap and water. For eye contact, flush immediately with plenty of water for at least 15 minutes. Consult physician immediately. For respiratory problems, remove person to fresh air.

ENVIRONMENTAL SAFETY PRECAUTIONS: (Industrial Use Only) Corrosive. Contains amines. Contact with eyes or skin may cause severe burns. Can cause sensitization after prolonged or repeated use. Use of safety goggles and chemical resistant gloves is highly recommended. Use with adequate ventilation.

WARRANTIES: Seller warrants that the Products do not infringe upon any copyright, patent, or trademark or trade secret, nor violate the proprietary information rights of any third party. Seller warrants that its Products will conform to and perform in accordance with the Products' specifications. THE FOREGOING WARRANTIES, ARE IN LIEU OF ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THOSE CONCERNING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. **LIMITATION ON LIABILITIES:** Because of the difficulty of ascertaining and measuring damages hereunder, it is agreed that, except for claims for bodily injury. Seller's liability to the Buyer or any third party, for any losses or damages, whether direct or otherwise, arising out of the purchase of Product from Seller by Buyer shall not exceed the total amount billed and billable to the Buyer for the Product hereunder. IN NO EVENT WILL SELLER BE LIABLE FOR ANY LOSS OF PROFITS OR OTHER SPECIAL OR CONSEQUENTIAL DAMAGES, EVEN IF SELLER HAS BEEN ADVISED OF THE POSSIBILITY OF SUCH DAMAGES.