

Product Technical Data Sheet

APPLICATIONS

- *Construction Adhesives*
- *Flooring and Mortars*
- *Laminates*
- *Low VOC Coatings*

FEATURES AND BENEFITS

- *Fast Cure Rate*
- *Does not contain Nonyl Phenol*
- *Does not contain Benzyl Alcohol*
- *Low Viscosity*
- *Excellent solvent resistance*
- *Ultra High Strength*



3835 State Route 72
Kirkland, Illinois 60146

www.epoxychemicals.com

Phone: 815-522-2308

FAX: 815-522-9041

e-mail: info@epoxychemicals.com

FS-943 POLYAMINE

FS-943 POLYAMINE is a low viscosity aliphatic amine adduct. Provides excellent mechanical properties, solvent and alcohol resistance when used with liquid and solid epoxy resins. Additionally can be used as a reactive accelerator with most amine curing agents for thermoset applications.

FS-943 POLYAMINE Properties

Appearance:	Clear Amber
Viscosity(cps)	3,500—4,500
Density(lbs/gal):	9.0
Equivalent Weight:	38
PHR, L.E.R.	20

Typical Properties

Liquid Epoxy Resin (189 EEW)	100
FS-943 POLYAMINE	20
Gel Time (200g.), mins	12
Tack Free, hours @ 75F	1-2
Through Cure, hours @ 75 F	2-3
Compressive Strength (ASTM D695), psi 7 Days (neat resin)	16,800

Data presented are typical laboratory values.

Product Technical Data Sheet



DISPOSAL: Collect with absorbent material. Dispose of in accordance with current local, state and federal regulations

FIRST AID: In case of skin contact, wash immediately and thoroughly with soap and water. For eye contact, flush immediately with plenty of water for at least 15 minutes. Consult physician immediately. For respiratory problems, remove person to fresh air.

ENVIRONMENTAL SAFETY PRECAUTIONS: (Industrial Use Only) Corrosive. Contains amines. Contact with eyes or skin may cause severe burns. Can cause sensitization after prolonged or repeated use. Use of safety goggles and chemical resistant gloves is highly recommended. Use with adequate ventilation.

WARRANTIES: Seller warrants that the Products do not infringe upon any copyright, patent, or trademark or trade secret, nor violate the proprietary information rights of any third party. Seller warrants that its Products will conform to and perform in accordance with the Products' specifications. THE FOREGOING WARRANTIES, ARE IN LIEU OF ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THOSE CONCERNING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. **LIMITATION ON LIABILITIES:** Because of the difficulty of ascertaining and measuring damages hereunder, it is agreed that, except for claims for bodily injury. Seller's liability to the Buyer or any third party, for any losses or damages, whether direct or otherwise, arising out of the purchase of Product from Seller by Buyer shall not exceed the total amount billed and billable to the Buyer for the Product hereunder. IN NO EVENT WILL SELLER BE LIABLE FOR ANY LOSS OF PROFITS OR OTHER SPECIAL OR CONSEQUENTIAL DAMAGES, EVEN IF SELLER HAS BEEN ADVISED OF THE POSSIBILITY OF SUCH DAMAGES.